



Low-alloy martensitic steel

F.A.R. QUALITY	TECHNOLOGICAL SPECIFICATIONS	HARDNESS		TYPE OF CASTINGS RECOMMENDED
		Min. HRC upon supply	Max. HRC upon supply	
F 60/5	Martensitic steel: it combines elevated hardness with good tenacity.	53	58	Hammers for recycling plants.

Analytical specifications

F.A.R. QUALITY		C %	Cr %	Ni %	Mo %
F 60/5	min:	0.45	4.00		0.30
	max:	0.55	6.50	0.50	0.50

Wear Parts in Steel qualities as above mentioned can also be produced with Ceramic-Inlays.